






# TECHNICKÝ LIST

CC

Version: 11/2022

Zloženie Composition	55% bavlna (z vnútra) / 45% polyester (z vonku)	
Plošná hmotnosť Weight	185 g/m <sup>2</sup>	Šírka Width 160-165 cm
Väzba Construction	Pletenina Knitted	piké, double face pique, double face

Údržba Care instruction	Pranie Washing	Bielenie Chlore	Sušenie Tumbler	Žehlenie Ironing	Chemické čistenie Dry cleaning
					

PARAMETER	METÓDA	HODNOTA	
Rozmerová zmena / Shrinkage after washing 5x pranie pri 60°C	EN ISO 6330	osnova/warp útok/weft	-1,0 / -4,5
Odpor proti prieniku vodných pár Ret / Water vapour resistance Ret	EN ISO 11092		3,07 m <sup>2</sup> Pa/W
Pevnosť pletenín pri pretrhnutí - Ø 50 mm <sup>2</sup> / Bursting strength	EN ISO 13938-2		188 kPa
Žmolkovanie / Pilling rating	EN ISO 12945-2	7000 cyklov	≥ 4
Odolnosť proti oderu Matindale / Martindale Abrasion resistance 9 kPa	EN ISO 12947-2	20 000 cyklov	bez dier not broken
Stálofarebnosť / Colour Fastness		zmena farby	zapustenie
vo svetle / to light	EN ISO 105-B02		
po praní 60°C / to washing	EN ISO 105-C06	4-5	4
pri otere za sucha / to rubbing-dry	EN ISO 105-X12	4-5	
pri otere za mokra / to rubbing-wet	EN ISO 105-X12	4-5	
v pote alkalickom /to perspiration alc.	EN ISO 105-E04	4-5	4
v pote kyslom / to perspiration acid.	EN ISO 105-E04	4-5	4
v žehlení 150°C / to ironing 150°C	EN ISO 105-X11	4-5	4

Vystavil: JNL s.r.o.

23.11.2022